



13055 15th Ave North
Plymouth MN, 55441
USA

www.nucoatinc.com

Technical Data Sheet

DIGITALL 9704 MIJ

Description: Product is normally used as very Durable Drum Label Coating. The coating is designed for pigment ink jet applications, but will also accept dye based ink systems. We recommend a starting coat weight of: 16 - 19#/3MSF.

Typical Properties:

Range:

pH	5.0 – 7.0
Solids	16.0 – 18.0%
Brookfield Viscosity (#1 spindle, 20 rpm, cps)	100 – 600
Density (Lbs./Gallon)	8.71#/Gal.
Specific Gravity	1.0471824
Appearance	White to Pale Yellow Liquid
VOC (excluding water)	4.78946% (by weight)

Features: Product shows excellent durability, water resistance, abrasion resistance, and some solvent resistance.

Packaging: 1, 5, 30, 55, 275 gallon containers, and bulk.

Recommended Storage Conditions: Store out of sunlight. Keep containers closed tightly. Store at temperatures of 35 - 85°F.

Shelf Life: 6 months under optimal storage conditions.

The information contained herein is believed to be reliable, but no representation, guarantees, or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made to the suitability of any use or handling of any material beyond NuCoat's direct control. The SELLER MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

This product is being provided to you under our non-analysis agreement in which you will not analyze for chemical composition nor physical structure. Final determinations on proper use of this product to fit the application(s), is the responsibility of the buyer